

# TYPE TPPB1L4

Made from high density polyethylene tapes and coated on two sides with low density polyethylene.  
Development Product (Temporary Data Sheet)

<u>PROPERTY</u>	<u>UNIT</u>		<u>VALUES</u>	<u>TEST METHOD</u>
Unit Weight	oz/yd2		3.4	ASTM D3776
Warp Construction	Tapes/in	Warp	9.1	ASTM D3775
		Weft	5.8	
Widths	in	up to	144	
Tensile Grab Strength	lbf	Warp	119	ASTM D751
		Weft	119	
Tear Strength * (tongue)	lbf	Warp	65	ASTM D2261
		Weft	53	
Tear Strength (trapezoid)	lbf	Warp	31	ASTM D4533
		Weft	31	
Coating	mil	Black	1	ASTM D1777 MOD
	mil	Tan	1.3	
Mullen Burst Strength	psi		181	ASTM D751
Nominal Thickness	mil		6	ASTM D1777 MOD

\* Includes force to shift tapes - Tear may be crosswise to direction of force.

---

Fabrene® TPPB1L4 contains some ultraviolet inhibitors and is suitable for short-term outdoor applications.  
For further information, contact your FABRENE Inc. representative.

---

Suggested Applications: Construction Tarps and General Purpose Tarps

NOTE: These values are typical data and are not intended as limiting specifications.

Date: 01/08/28